


ADLER Aquacryl CFB

30090 ff



10 %

Product description

Water-thinnable clear varnish on an acrylate dispersion basis for wood in internal areas, can be applied varnish-on-varnish, good mechanical and chemical resistance, very good body.

Special features

Resistance to cream and grease.
The requirements of Evaluation Class 5-B in accordance with ÖNORM [Austrian Standard] A1605-12 for hardly inflammable furniture surfaces are fulfilled.

Fields of application

Wall and ceiling wainscoting, panels, wooden furniture, doors (use seals which are suitable for water-based varnishes!) and children's toys.

Also suitable for renovation coatings on conventional furniture varnishes.

ADLER Aquacryl CFB must not be used on water-based stains.

Method of application

Brushing (acrylic brush) and spraying (airless, compressed air)

Substrate preparation

New coat - sand with 180 grain
Renovation coat - sand with 280 – 320 grain

New coat

2 – 3 x with ADLER Aquacryl CFB
(Intermediate sanding with 280 – 320 grain)

For tongue and groove boards, in principle, we recommend painting before assembly. If this is not possible, apply only a little varnish in the tongue and groove areas in order to avoid adhesions.

Renovation coat

1 x ADLER Aquacryl CFB
(sand beforehand with 280 – 320 grain)

Thinner

Water
Brushing & airless spraying - Unthinned
Spraying with compressed air - About 10 %
gun

Application and object temperatures

Not under + 10 °C
High air humidity and/or low temperatures delay drying.

Drying time (20 °C)

Can be sanded and painted over after about 2 hours

01-07 (replaces 03-05)

ADLER-Werk Lackfabrik, A-6130 Schwaz, 05242/6922-303

Our instructions are based on the current state of knowledge and should inform the buyer/user to the best of our knowledge. They are, however, not binding and are to be suited to the field of application and the working conditions. The buyer/user decides on his own responsibility about the suitability and employment of the delivered product. In addition there apply our General Terms of Sale. With this issue, all previous information sheets are no longer applicable. Changes are reserved for packaging sizes, colour shades and available glosses

Work equipment

Clean with water immediately after use. Then dry spraying equipment well in order to prevent rusting. Remove remains of dried-on varnish with ADLER Abbeizer [*stain remover*].

Application quantity (per application)10 - 12 m²/l**Supplied sizes**

125 ml, 375 ml, 750 ml, 2.5 l

Storage

Cool but frost-free

Storage life

3 years in unopened drums

Degrees of gloss

G 100 gloss	30090
G 30 matt	30093
G 50 semi-matt	30095

Safety information**Please refer to the Safety Data Sheet**

Even when working with varnishes which are low in harmful substances, the usual protective measures are to be observed.