

ADLER Aqua-Isoprimer PRO 41005

Water-based primer and intermediate coat for wood in internal and external areas with excellent insulation efficiency for **DIY and professional use**

PRODUCT DESCRIPTION

General

Water-based, white primer and intermediate coat on a special acrylate-dispersion base. The product is formulated without addition of biocidal active substances as protection against blue stain and wood-destroying fungi.

Special Properties and standards

- High insulation property for wood extractives and dry water stains.
- High elasticity and body
- Excellent processing and flow
- Environmentally friendly and odourless
- **French Ordinance DEVL1104875A** regarding the labelling of construction coating products with respect to their emission of volatile pollutants: A+



Application area

Wood in internal and external areas.




PROCESSING

Instructions for use



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least + 10 °C.
- The optimal conditions for processing or use lie between 15 – 25 °C at relative atmospheric humidity from 40 - 80 %.
- Minor quantities of application and/or stronger dilution will reduce the insulation effect!
- Depending on the species of wood but also on the growing region, the content of the colouring water-soluble wood extractives may vary significantly. It is therefore recommended to test always the coating on a specimen of the original wood in order to judge the insulation effect.
- Overnight drying consolidates the insulation effect.

Application technique

Application method	Using a brush	Roller brush application	Cup gun
Spray nozzle (ø mm)	-	-	1.8 - 2
Spraying pressure (bar)	-	-	2 – 2.5
Thinner	water		
Thinner amount added in %	max. 5		max. 20
Yield per application (m ² /l) ¹⁾	8 - 10		
¹⁾ Yield including addition of thinner and loss while spraying			

The product is prepared such that it is ready to use.

The properties and type of the substrate affect the consumption / yield. Accurate values for consumption must be obtained by applying trial coats in advance

Drying times

(at 20 °C room temperature)




Can be sanded	after 4 hours
Can be recoated	after 4 hours

The figures indicated serve as a guide and are for reference. The drying time depends on the substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and / or high level of atmospheric humidity can increase the drying time considerably.

Avoid direct sunlight (very quick drying).

Cleaning the tools and equipment

With water immediately after use.

Remove dried-up paint residues with ADLER Abbeizer Rote Krähe 95125.

SUBSTRATE**Type of substrate**

Wood, wood-based materials as well as stable wood coatings

Substrate property (or condition)

The substrate must be dry, clean and free from any separating substances (wax, grease), and it must be tested for suitability and stability.

Please observe ÖNORM B 2230 Part 2.

See also VOB, Part C, DIN 18363, paragraph 3; Painting and coating work.

Please observe BFS-data sheet No. 18.

The prerequisite for long storage stability of the coating is compliance with the principles of the constructive wood preservation.

Any coatings that cannot be recoated must be removed thoroughly.

Wood moisture

Hardwoods: 12 % +/- 2 %

Softwoods: 15 % +/- 2 %.

Preparation of the substrate**Wood and wooden materials indoors**

Break off sharp edges and remove any wood extractives such as resins and resin pockets, for example.

Grain size for sanding the wood 120 – 150

Wood, external wood protection

For optimal storage stability, we recommend smooth wooden surfaces are sanded with grain size 80 in the direction of the fibre, cleaned thoroughly and wood extractives such as, for example, resins and resin pockets are removed. Round off any sharp edges.

Clean woods having high resin content and exotic types of woods having constituents that delay the drying process with ADLER Nitroverdünnung 80001.

Treat infestation or attack by algae, moss or fungus with ADLER Fungisan 96349.

Old coats

Sand with grain size 120 and clean the surface. Remove any old coats that cannot be recoated.

Please follow the respective data sheets of the products.

COATING SYSTEM**Impregnation**

Apply 1 coat of Pullex Aqua-Imprägnierung (primer) 51320 ff to protect against blue stain, fungal and insect attack (applies to wood of the durability class according to EN 350-2, 3 – 5).

Primer coat

1 - 2 x ADLER Aqua-Isoprimer PRO 41005

Intermediate drying time: approx. 4 hours

Overnight drying consolidates the insulation effect.

Please follow the respective technical data sheets of the products.

Intermediate sanding

Sand the primer coated surface with grain size 240. Remove the wood dust.

Use dust filter P2 while sanding or grinding.

Final coat

2 x ADLER Aqua-PU PRO 41231 ff

or

1 x Pullex Aqua-Color W10 Weiß (white) 53331

Please follow the respective technical data sheets of the products.

ORDERING INFORMATION**Size of trading unit**

750 ml; 2.5 l and 10 l

Colour / Degree of gloss

Weiß/white

Supplementary products

ADLER Abbeizer Rote Krähe 95125

ADLER Fungisan 96349

Pullex Aqua-Imprägnierung 51320

Pullex Aqua-Color W10 Weiß 53331

ADLER Aqua-PU PRO 41231 ff

ADLER Nitroverdünnung 80001

FURTHER DETAILS

Durability / Storage

3 years in the original sealed containers.

Store it such that it is protected against moisture, direct sunlight, frost and high temperatures (over 30°C).

Technical specifications

VOC content

EU limit value for ADLER Aqua-Isoprimer PRO (Cat. A/g): 30 g/l (2010). ADLER Aqua-Isoprimer PRO contains maximum 30 g/l VOC.

Product code for paints and varnishes

M-GP01

Safety-relevant information

Please follow the associated safety data sheet! The latest version can be retrieved from the Internet at **www.adler-lacke.com**.

In general, you must avoid inhaling paint aerosols. This is ensured by proper use of a breathing mask (combination filter A2/P2 – EN 141/EN 143).
