


Aquawood-Fensterlasur VAC

59130



Product description

Water-thinnable translucent wood finish for windows, based on acrylate dispersions, with high transparency, high anti-blocking properties and fast water resistance. Very good body due to a high solid. The coating system is protected from the attack of blue stain fungus and mould formation.

Fields of application

Wooden windows, especially for wood-aluminium constructions, not suited for direct exposure to the weathering.

Application

Vacumat

Coating system

Softwood:

1 x Aquawood-Tiefenimprägnierung AC 57952

4 hours drying

2 x Aquawood Fensterlasur VAC 59130, wet film thickness:
90 – 100 µm each

Compatibility with sealant-material

Use only controlled types ! Liste with suited silicones available.

Dilution

Water, of necessary

Drying time (room temperature 20°C)

Dust dry	after approx. 30 min
Tack-free	after approx. 3 hours
Completely dry	after approx. 12 hours

Application and object temperature

Not less than + 10 °C
High air humidity and/or low temperatures retard the drying time. Avoid direct sunlight.

Tools

Clean with water immediately after use. Remove dried-on residue of paint with ADLER Aqua-Cleaner or ADLER Abbeizer (Paint Remover).

Spreading rate

approx. 100 g/m² and application

Packaging size

25 kg

Continuation

Aquawood-Fensterlasur VAC 59130

Storage

Cool, but frost-free

Shelf life

1 year in original closed cans

Special instructions

Please observe our Working Guidelines for Wooden Window Coating with the spraying Method and all Standards and Directives concerning window construction!

Safety information

Please pay attention to the Safety Data Sheet!