

## ADLER Hirnholzversiegelung

**55621**



### Product description

Water dilutable filler based on acrylate dispersion with excellent water resistance. Prevents the capillary absorption of water via cross-cut wood.

Excellent filling power and quick drying. Free of solvents. For transparent and covering coatings systems. The coat is protected from blue stain fungi and fungal decay.

### Application area

Cross-cut wood of windows and doors (glazing bars and V-shaped joints), millings of facing panels and garage-doors.

### Application method

Rolling, painting, spraying (airless, airmix)

### Coating system

After the application of the primer and intermediate coating apply 1-2 coats of ADLER Hirnholzversiegelung 55621 (intermediate drying time 2 hours), before applying the top coat.

### Thinner

Use undiluted

### Application and substrate temperature

Not below + 10 °C

High air humidity and/or low temperatures may increase the drying time.

### Drying time (room temperature 20 °C)

Approx. 2 hours

### Working equipment

Clean with water immediately after use.

Remove flashed-off coat residues using ADLER Aqua-Cleaner 80080 or ADLER Abbeizer Rote Krähe (Red Crow) 95125.

### Container sizes

750 g; 3 kg; 5 kg and 25 kg

### Storage

Cool, but frost-free

### Durability

1 year in the original sealed containers.