

Pigmofix V

8118

Retarder for glass coating using a paint roller for professional and industrial use

PRODUCT DESCRIPTION

Product numbers

8118000210

General

Special solvent mixture for optimising the workability of the mixture of Aduro Pigmopur (2406) / Pigmofix G and PUR-Hardener (8419) by delaying drying when coating glass backsides with a paint roller is required.

Application area



As an additive to Pigmopur G50 (2406) for coating the backsides of glass components whose edges are protected from direct contact with moisture due to construction (e.g. wooden frames), using a paint roller.

The product does not affect the surface quality of the coating system (chemical and mechanical resistance)

PROCESSING

Processing instructions

- Carefully stir Pigmofix V (8118) into the hardened varnish.
- Use a paint roller for application (short haired roller – see supplementary products).
- Paints/varnishes that have been mixed can be used as explained in the relevant technical data sheet.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result.
- Please follow our **ARL 143 - Working guidelines for the back-side coating of glass with furniture coatings.**

Quantity to be added



Mixing ratio	
Pigmopur (2406) in the desired colour shade	100% by weight
Pigmofix G 90699	5% by weight
PUR-Hardener 8419 (8419)	20% by weight
Pigmofix V (8118)	10 - 20% by weight

Cleaning the working equipment

8519



8501

With DD-Verdünnern 8519 (8519) or Waschverdünner (8501) immediately after use.

ORDERING INFORMATION**Size of trading unit**

400 ml, 10 l

Supplementary products

DD-Verdünnern 8519 (8519)
Pigmofix G (90699)
Pigmopur G50 (2406)
PUR-Hardener 8419 (8419)
Waschverdünner 8501 (8501)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS**Durability / storage**

Min. 2 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Safety information

The product is only suitable for the industrial and professional use.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at **www.adler-lacke.com**.